


NdFeB

NEOREM 595t

B_r NOMINAL VALUES / J_c NOMINAL VALUES



neorem
magnets



Typical demagnetization curves B(H) and J(H) at different temperatures

Remanence B_r [T]	
nom	min
1.16	1.12

Normal coercivity H_c [kA/m]	
nom	min
890	830

Intrinsic coercivity H_c [kA/m]	
nom	min
2400	2100

Energy product $(BH)_{max}$ [kJ/m ³]	
nom	min
260	240