


NdFeB

NEOREM 737a

B_r NOMINAL VALUES / J_c NOMINAL VALUES



neorem
magnets



Typical demagnetization curves B(H) and J(H) at different temperatures

Remanence B_r [T]	
nom	min
1.30	1.26

Normal coercivity H_c [kA/m]	
nom	min
990	940

Intrinsic coercivity H_c [kA/m]	
nom	min
1350	1200

Energy product $(BH)_{max}$ [kJ/m ³]	
nom	min
320	300