


NdFeB

NEOREM 795a

B_r NOMINAL VALUES / J_c NOMINAL VALUES



neorem
magnets



Remanence B_r [T]	
nom	min
1.16	1.12

Normal coercivity H_c [kA/m]	
nom	min
890	830

Intrinsic coercivity H_c [kA/m]	
nom	min
2400	2100

Energy product $(BH)_{max}$ [kJ/m ³]	
nom	min
250	240