


NdFeB

NEOREM 799a

B_r NOMINAL VALUES / J_c NOMINAL VALUES



Typical demagnetization curves B(H) and J(H) at different temperatures

Remanence B_r [T]	
nom	min
1.08	1.04

Normal coercivity H_c [kA/m]	
nom	min
830	770

Intrinsic coercivity J_c [kA/m]	
nom	min
3200	3000

Energy product $(BH)_{max}$ [kJ/m ³]	
nom	min
220	200