


NdFeB

NEOREM 753t

B_r NOMINAL VALUES / J_c NOMINAL VALUES



Typical demagnetization curves B(H) and J(H) at different temperatures

Remanence B_r [T]	
nom	min
1.33	1.30

Normal coercivity H_c [kA/m]	
nom	min
1010	960

Intrinsic coercivity H_c [kA/m]	
nom	min
1500	1400

Energy product (BH) _{max} [kJ/m ³]	
nom	min
330	320