


NdFeB

# NEOREM 795t

$B_r$  NOMINAL VALUES /  $J_c$  NOMINAL VALUES



**neorem  
magnets**



Typical demagnetization curves B(H) and J(H) at different temperatures

Remanence $B_r$ [T]	
nom	min
1.20	1.17

Normal coercivity $H_c$ [kA/m]	
nom	min
920	870

Intrinsic coercivity $H_c$ [kA/m]	
nom	min
2400	2100

Energy product $(BH)_{max}$ [kJ/m <sup>3</sup> ]	
nom	min
270	260