


NdFeB

NEOREM 880a

B_r NOMINAL VALUES / J_c NOMINAL VALUES



neorem
magnets



Typical demagnetization curves B(H) and J(H) at different temperatures

Remanence B_r [T]	
nom	min
1.26	1.23

Normal coercivity H_c [kA/m]	
nom	min
960	910

Intrinsic coercivity H_{ci} [kA/m]	
nom	min
2100	2000

Energy product $(BH)_{max}$ [kJ/m ³]	
nom	min
300	290