


NdFeB

NEOREM 576a

B_r NOMINAL VALUES / J_c NOMINAL VALUES



Typical demagnetization curves B(H) and J(H) at different temperatures

Remanence B_r [T]	
nom	min
1.22	1.18

Normal coercivity H_c [kA/m]	
nom	min
930	880

Intrinsic coercivity H_c [kA/m]	
nom	min
1750	1550

Energy product $(BH)_{max}$ [kJ/m ³]	
nom	min
280	260