


NdFeB

NEOREM 593t

B_r NOMINAL VALUES / J_c NOMINAL VALUES



neorem
magnets



Typical demagnetization curves $B(H)$ and $J(H)$ at different temperatures

Remanence B_r [T]	
nom	min
1.20	1.15

Normal coercivity H_c [kA/m]	
nom	min
910	850

Intrinsic coercivity H_{ci} [kA/m]	
nom	min
2100	1800

Energy product $(BH)_{max}$ [kJ/m ³]	
nom	min
270	250