


NdFeB

NEOREM 880t

B_r NOMINAL VALUES / J_c NOMINAL VALUES



Typical demagnetization curves B(H) and J(H) at different temperatures

Remanence B_r [T]	
nom	min
1.29	1.26

Normal coercivity H_c [kA/m]	
nom	min
990	940

Intrinsic coercivity H_{ci} [kA/m]	
nom	min
2100	2000

Energy product (BH) _{max} [kJ/m ³]	
nom	min
320	300