


NdFeB

# NEOREM 737a

$B_r$  NOMINAL VALUES /  $J_H$  NOMINAL VALUES



Typical demagnetization curves B(H) and J(H) at different temperatures

Remanence $B_r$ [T]	
nom	min
1,30	1,26

Normal Coercivity $B_H H_c$ [kA/m]	
nom	min
990	940

Intrinsic Coercivity $J_H H_c$ [kA/m]	
nom	min
1350	1200

Energy Product $(BH)_{max}$ [kJ/m <sup>3</sup> ]	
nom	min
320	300