



NdFeB

# NEOREM 776t mod

$B_r$  NOMINAL VALUES /  $J_H$  NOMINAL VALUES



Remanence $B_r$ [T]	
nom	min
1,32	1,30

Normal Coercivity $BH_c$ [kA/m]	
nom	min
1010	970

Intrinsic Coercivity $J_H$ [kA/m]	
nom	min
1700	1600

Energy Product $(BH)_{max}$ [kJ/m <sup>3</sup> ]	
nom	min
330	320

Typical demagnetization curves B(H) and J(H) at different temperatures