


NdFeB

# NEOREM 830a

$B_r$  NOMINAL VALUES /  $J_H$  NOMINAL VALUES



Remanence $B_r$ [T]	
nom	min
1,32	1,29

Normal Coercivity $B_H$ [kA/m]	
nom	min
1010	960

Intrinsic Coercivity $J_H$ [kA/m]	
nom	min
1400	1350

Energy Product $(BH)_{max}$ [kJ/m <sup>3</sup> ]	
nom	min
330	320

Typical demagnetization curves B(H) and J(H) at different temperatures