


NdFeB

NEOREM 870a

B_r NOMINAL VALUES / J_H NOMINAL VALUES



Remanence B_r [T]	
nom	min
1,30	1,27

Normal Coercivity $B_H H_c$ [kA/m]	
nom	min
990	940

Intrinsic Coercivity $J_H H_c$ [kA/m]	
nom	min
1700	1600

Energy Product $(BH)_{max}$ [kJ/m ³]	
nom	min
320	310

Typical demagnetization curves B(H) and J(H) at different temperatures