


NdFeB

NEOREM 537a

B_r NOMINAL VALUES / J_H NOMINAL VALUES



Typical demagnetization curves B(H) and J(H) at different temperatures

Remanence B_r [T]	
nom	min
1,28	1,24

Normal Coercivity B_H [kA/m]	
nom	min
980	920

Intrinsic Coercivity J_H [kA/m]	
nom	min
1350	1200

Energy Product $(BH)_{max}$ [kJ/m ³]	
nom	min
310	290