


NdFeB

NEOREM 537t

B_r NOMINAL VALUES / J_H NOMINAL VALUES



Remanence B_r [T]	
nom	min
1,32	1,27

Normal Coercivity $B_B H_c$ [kA/m]	
nom	min
1000	940

Intrinsic Coercivity J_H [kA/m]	
nom	min
1350	1200

Energy Product $(BH)_{max}$ [kJ/m ³]	
nom	min
330	310

Typical demagnetization curves B(H) and J(H) at different temperatures