


NdFeB

NEOREM 595a

B_r NOMINAL VALUES / J_H NOMINAL VALUES



Remanence B_r [T]	
nom	min
1,13	1,09

Normal Coercivity BH_c [kA/m]	
nom	min
860	810

Intrinsic Coercivity JH_c [kA/m]	
nom	min
2400	2100

Energy Product $(BH)_{max}$ [kJ/m ³]	
nom	min
240	230

Typical demagnetization curves B(H) and J(H) at different temperatures