


NdFeB

NEOREM 599t

B_r NOMINAL VALUES / J_H NOMINAL VALUES



Typical demagnetization curves B(H) and J(H) at different temperatures

Remanence B_r [T]	
nom	min
1,08	1,03

Normal Coercivity BH_c [kA/m]	
nom	min
820	760

Intrinsic Coercivity J_H [kA/m]	
nom	min
3200	3000

Energy Product $(BH)_{max}$ [kJ/m ³]	
nom	min
220	200