


NdFeB

NEOREM 799a

B_r NOMINAL VALUES / J_H NOMINAL VALUES



Remanence B_r [T]	
nom	min
1,08	1,04

Normal Coercivity BH_c [kA/m]	
nom	min
820	770

Intrinsic Coercivity J_H [kA/m]	
nom	min
3200	3000

Energy Product $(BH)_{max}$ [kJ/m ³]	
nom	min
220	210

Typical demagnetization curves B(H) and J(H) at different temperatures