


NdFeB

# NEOREM 890a

$B_r$  NOMINAL VALUES /  $J_H$  NOMINAL VALUES



Remanence $B_r$ [T]	
nom	min
1,24	1,21

Normal Coercivity $BH_c$ [kA/m]	
nom	min
950	900

Intrinsic Coercivity $J_H$ [kA/m]	
nom	min
2350	2250

Energy Product $(BH)_{max}$ [kJ/m <sup>3</sup> ]	
nom	min
290	280