


NdFeB

# NEOREM 512t

$B_r$  NOMINAL VALUES /  $J_H$  NOMINAL VALUES



Remanence $B_r$ [T]	
nom	min
1,35	1,30

Normal Coercivity $B_H$ [kA/m]	
nom	min
1030	970

Intrinsic Coercivity $J_H$ [kA/m]	
nom	min
1120	1050

Energy Product $(BH)_{max}$ [kJ/m <sup>3</sup> ]	
nom	min
350	320

Typical demagnetization curves B(H) and J(H) at different temperatures