


NdFeB

# NEOREM 576a

$B_r$  NOMINAL VALUES /  $J_H$  NOMINAL VALUES



Remanence $B_r$ [T]	
nom	min
1,22	1,18

Normal Coercivity $B_H$ [kA/m]	
nom	min
930	880

Intrinsic Coercivity $J_H$ [kA/m]	
nom	min
1750	1550

Energy Product $(BH)_{max}$ [kJ/m <sup>3</sup> ]	
nom	min
280	270

Typical demagnetization curves B(H) and J(H) at different temperatures