


NdFeB

# NEOREM 593t

$B_r$  NOMINAL VALUES /  $J_H$  NOMINAL VALUES



Remanence $B_r$ [T]	
nom	min
1,20	1,15

Normal Coercivity $B_H H_c$ [kA/m]	
nom	min
910	850

Intrinsic Coercivity $J_H H_c$ [kA/m]	
nom	min
2100	1800

Energy Product $(BH)_{max}$ [kJ/m <sup>3</sup> ]	
nom	min
270	250

Typical demagnetization curves B(H) and J(H) at different temperatures