


NdFeB

# NEOREM 595t

$B_r$  NOMINAL VALUES /  $J_H$  NOMINAL VALUES



Typical demagnetization curves B(H) and J(H) at different temperatures

Remanence $B_r$ [T]	
nom	min
1,16	1,12

Normal Coercivity $BH_c$ [kA/m]	
nom	min
890	830

Intrinsic Coercivity $J_H$ [kA/m]	
nom	min
2400	2100

Energy Product $(BH)_{max}$ [kJ/m <sup>3</sup> ]	
nom	min
260	240