


NdFeB

NEOREM 599a

B_r NOMINAL VALUES / J_H NOMINAL VALUES



Typical demagnetization curves B(H) and J(H) at different temperatures

Remanence B_r [T]	
nom	min
1,05	1,00

Normal Coercivity $B_H H_c$ [kA/m]	
nom	min
800	740

Intrinsic Coercivity $J_H H_c$ [kA/m]	
nom	min
3200	3000

Energy Product $(BH)_{max}$ [kJ/m ³]	
nom	min
210	190