


NdFeB

# NEOREM 793a

$B_r$  NOMINAL VALUES /  $J_H$  NOMINAL VALUES



Typical demagnetization curves B(H) and J(H) at different temperatures

Remanence $B_r$ [T]	
nom	min
1,21	1,17

Normal Coercivity $H_c$ [kA/m]	
nom	min
930	870

Intrinsic Coercivity $J_H$ [kA/m]	
nom	min
2100	1800

Energy Product $(BH)_{max}$ [kJ/m <sup>3</sup> ]	
nom	min
280	260