


NdFeB

NEOREM 795t

B_r NOMINAL VALUES / J_H NOMINAL VALUES



Remanence B_r [T]	
nom	min
1,20	1,17

Normal Coercivity BH_c [kA/m]	
nom	min
920	870

Intrinsic Coercivity J_H [kA/m]	
nom	min
2400	2100

Energy Product $(BH)_{max}$ [kJ/m ³]	
nom	min
270	260

Typical demagnetization curves B(H) and J(H) at different temperatures