


NdFeB

# NEOREM 799t

$B_r$  NOMINAL VALUES /  $J_H$  NOMINAL VALUES



Typical demagnetization curves B(H) and J(H) at different temperatures

Remanence $B_r$ [T]	
nom	min
1,12	1,09

Normal Coercivity $B_H$ [kA/m]	
nom	min
860	810

Intrinsic Coercivity $J_H$ [kA/m]	
nom	min
3200	3000

Energy Product $(BH)_{max}$ [kJ/m <sup>3</sup> ]	
nom	min
240	220