


NdFeB

# NEOREM 820t

$B_r$  NOMINAL VALUES /  $J_H$  NOMINAL VALUES



Remanence $B_r$ [T]	
nom	min
1,40	1,37

Normal Coercivity $BH_c$ [kA/m]	
nom	min
1070	1020

Intrinsic Coercivity $JH_c$ [kA/m]	
nom	min
1200	1100

Energy Product $(BH)_{max}$ [kJ/m <sup>3</sup> ]	
nom	min
370	360

Typical demagnetization curves B(H) and J(H) at different temperatures