


NdFeB

# NEOREM 890t

$B_r$  NOMINAL VALUES /  $J_H$  NOMINAL VALUES



Typical demagnetization curves  $B(H)$  and  $J(H)$  at different temperatures

Remanence $B_r$ [T]	
nom	min
1,27	1,24

Normal Coercivity $BH_c$ [kA/m]	
nom	min
970	920

Intrinsic Coercivity $J_H$ [kA/m]	
nom	min
2350	2250

Energy Product $(BH)_{max}$ [kJ/m <sup>3</sup> ]	
nom	min
310	290